



Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4379$ $y=0.3983$ / $u'=0.2537$ $v'=0.5193$ $duv=-3.996e-003$
 Tc=2936K Dominant WL:Ld=584.0nm Purity=51.0%
 Ratio:R=26.8% G=70.4% B=2.8% Peak WL:Lp=629.7nm HWL:169.5nm
 Render Index:Ra=96.9 [暖白]
 R1 =99 R2 =99 R3 =98 R4 =97 R5 =99 R6 =97 R7 =95
 R8 =92 R9 =84 R10=97 R11=96 R12=88 R13=99 R14=98 R15=97

Photo Parameters:

$e=1.749e-002$ umol/s blue ratio=8.27 fluo. eff.= $1.692e-002$
 Flux = 18.43 lm Eff. : 99.80 lm/W Fe = 35.02 mW

Electrical parameters:



VF = 3.083 V IF = 59.90 mA P = 184.7 mW Ch1
 LEVEL:528 WHITE:OUT

Status: T=419.00ms Ip=60003 (92%) [HAAS2000_V1_USB] V2.00.167

Model:2835
 Tester:
 Temperature:25.3Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:N 28230
 Date:2018-05-21
 Humidity:65.0%
 Remarks:0

Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4335$ $y=0.3955$ $u'=0.2521$ $v'=0.5174$ $duv=-4.571e-003$
 Tc=2987K Dominant WL:Ld=584.0nm Purity=48.8%
 Ratio:R=26.5% G=70.6% B=2.9% Peak WL:Lp=628.5nm HWL:171.6nm
 Render Index:Ra=96.9 [暖白]
 R1 =99 R2 =99 R3 =97 R4 =97 R5 =99 R6 =96 R7 =95
 R8 =93 R9 =85 R10=97 R11=96 R12=88 R13=99 R14=98 R15=98

Photo Parameters:

$e=1.653e-002$ umol/s blue ratio=7.81 fluo. eff.=1.594e-002

Flux = 17.46 lm Eff. : 94.62 lm/W Fe = 33.17 mW

Electrical parameters:

VF = 3.080 V IF = 59.90 mA P = 184.5 mW Ch1

LEVEL:528 WHITE:OUT

Status: T=419.00ms Ip=56175 (86%) [HAAS2000_V1_USB] V2.00.167

Model:2835
 Tester:
 Temperature:25.3Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:N 28231
 Date:2018-05-21
 Humidity:65.0%
 Remarks:0