



Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4629$ $y=0.4078$ / $u'=0.2657$ $v'=0.5267$ $duv=-1.180e-003$
 Tc=2637K Dominant WL:Ld=585.0nm Purity=61.3%
 Ratio:R=26.7% G=71.0% B=2.2% Peak WL:Lp=604.9nm HWL:107.8nm
 Render Index:Ra=81.5 [暖白同1]
 R1 =81 R2 =93 R3 =93 R4 =79 R5 =81 R6 =93 R7 =79
 R8 =54 R9 =1 R10=84 R11=79 R12=78 R13=84 R14=97 R15=72

Photo Parameters:

$e=9.336e-003$ umol/s blue ratio=8.57 fluo. eff.=2.738e-002
 Flux = 6.731 lm Eff. : 107.61 lm/W Fe = 19.11 mW

Electrical parameters:



VF = 3.127 V IF = 20.00 mA P = 62.55 mW Ch1
 LEVEL:Class3 WHITE:ANSI_2700K

Status: T=446.00ms Ip=42762 (65%) [HAAS2000_V1_USB] V2.00.220

Model:3528
 Tester:
 Temperature:25Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:14
 Date:2018-05-20 10-48
 Humidity:45%
 Remarks:

Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4609$ $y=0.4051$ / $u'=0.2657$ $v'=0.5254$ $duv=-2.039e-003$
 Tc=2642K Dominant WL:Ld=585.2nm Purity=59.9%
 Ratio:R=26.7% G=71.1% B=2.2% Peak WL:Lp=604.6nm HWL:107.8nm
 Render Index:Ra=81.5 [暖白同1]
 R1 =81 R2 =93 R3 =93 R4 =79 R5 =82 R6 =92 R7 =79
 R8 =54 R9 =2 R10=84 R11=79 R12=78 R13=84 R14=97 R15=72

Photo Parameters:

$e=9.188e-003$ umol/s blue ratio=8.25 fluo. eff.=2.691e-002
 Flux = 6.602 lm Eff. : 105.75 lm/W Fe = 18.83 mW

Electrical parameters:

VF = 3.121 V IF = 20.00 mA P = 62.43 mW Ch1
 LEVEL:Class3 WHITE:ANSI_2700K

Status: T=561.00ms Ip=52466 (80%) [HAAS2000_V1_USB] V2.00.220

Model:3528
 Tester:
 Temperature:25Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:15
 Date:2018-05-20 10-48
 Humidity:45%
 Remarks: