



Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4425$ $y=0.4059$ / $u'=0.2534$ $v'=0.5229$ $duv=4.705e-004$
 Tc=2924K Dominant WL:Ld=583.2nm Purity=54.6%
 Ratio:R=24.2% G=73.6% B=2.2% Peak WL:Lp=603.9nm HWL:128.1nm
 Render Index:Ra=81.7 [暖白同1]
 R1 =80 R2 =90 R3 =97 R4 =80 R5 =80 R6 =88 R7 =82
 R8 =57 R9 =1 R10=77 R11=80 R12=70 R13=82 R14=99 R15=72

Photo Parameters:

$e=9.075e-003$ umol/s blue ratio=7.29 fluo. eff.=2.669e-002

Flux = 6.740 lm Eff. : 108.93 lm/W Fe = 18.78 mW

Electrical parameters:

VF = 3.094 V IF = 20.00 mA P = 61.88 mW Ch1



LEVEL:Class3 WHITE:ANSI_3000K

Status: T=561.00ms Ip=48812 (74%) [HAAS2000_V1_USB] V2.00.220

Model:3528
 Tester:
 Temperature:25Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:16
 Date:2018-05-20 10-49
 Humidity:45%
 Remarks:

Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4368$ $y=0.4029$ / $u'=0.2510$ $v'=0.5209$ $duv=1.268e-004$
 Tc=2992K Dominant WL:Ld=583.0nm Purity=52.1%
 Ratio:R=23.9% G=73.8% B=2.4% Peak WL:Lp=603.4nm HWL:131.5nm
 Render Index:Ra=82.4 [暖白同1]
 R1 =81 R2 =90 R3 =97 R4 =81 R5 =81 R6 =88 R7 =83
 R8 =59 R9 =4 R10=78 R11=80 R12=70 R13=83 R14=99 R15=73

Photo Parameters:

$e=9.150e-003$ umol/s blue ratio=6.78 fluo. eff.= $2.728e-002$

Flux = 6.782 lm Eff. : 111.80 lm/W Fe = 18.98 mW

Electrical parameters:

VF = 3.033 V IF = 20.00 mA P = 60.66 mW Ch1

LEVEL:Class3 WHITE:ANSI_3000K

Status: T=561.00ms Ip=48507 (74%) [HAAS2000_V1_USB] V2.00.220

Model:3528
 Tester:
 Temperature:25Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:17
 Date:2018-05-20 10-50
 Humidity:45%
 Remarks: