



Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4543$ $y=0.4059$ / $u'=0.2610$ $v'=0.5247$ $duv=-1.056e-003$
 Tc=2742K Dominant WL:Ld=584.4nm Purity=58.2%
 Ratio:R=26.9% G=70.9% B=2.2% Peak WL:Lp=627.6nm HWL:162.9nm
 Render Index:Ra=92.9 [暖白同1]
 R1 =93 R2 =96 R3 =96 R4 =93 R5 =93 R6 =94 R7 =93
 R8 =84 R9 =65 R10=89 R11=94 R12=82 R13=94 R14=97 R15=90

Photo Parameters:

$e=9.403e-003$ umol/s blue ratio=9.68 fluo. eff.= $2.716e-002$
 Flux = 5.602 lm Eff. : 89.21 lm/W Fe = 18.81 mW

Electrical parameters:



VF = 3.140 V IF = 20.00 mA P = 62.80 mW Ch1
 LEVEL:Class3 WHITE:ANSI_2700K

Status: T=798.00ms Ip=57051 (87%) [HAAS2000_V1_USB] V2.00.220

Model:3528
 Tester:
 Temperature:25Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:6
 Date:2018-05-20 10-39
 Humidity:45%
 Remarks:

Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4520$ $y=0.4018$ / $u'=0.2613$ $v'=0.5228$ $duv=-2.364e-003$
 Tc=2744K Dominant WL:Ld=584.9nm Purity=56.3%
 Ratio:R=26.9% G=70.8% B=2.2% Peak WL:Lp=622.9nm HWL:162.1nm
 Render Index:Ra=92.9 [暖白同1]
 R1 =94 R2 =96 R3 =96 R4 =93 R5 =93 R6 =94 R7 =93
 R8 =85 R9 =65 R10=89 R11=94 R12=83 R13=94 R14=97 R15=91

Photo Parameters:

$e=9.258e-003$ umol/s blue ratio=9.18 fluo. eff.=2.672e-002

Flux = 5.505 lm Eff. : 87.93 lm/W Fe = 18.55 mW

Electrical parameters:

VF = 3.130 V IF = 20.00 mA P = 62.61 mW Ch1

LEVEL:Class3 WHITE:ANSI_2700K

Status: T=798.00ms Ip=56279 (86%) [HAAS2000_V1_USB] V2.00.220

Model:3528
 Tester:
 Temperature:25Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:7
 Date:2018-05-20 10-39
 Humidity:45%
 Remarks: