



Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4682$ $y=0.4105$ $u'=0.2680$ $v'=0.5286$ $duv=-6.439e-004$
 Tc=2586K Dominant WL:Ld=585.0nm Purity=63.8%
 Ratio:R=28.1% G=70.1% B=1.9% Peak WL:Lp=627.6nm HWL:153.3nm
 Render Index:Ra=91.8 [暖白同1]
 R1 =92 R2 =95 R3 =96 R4 =92 R5 =92 R6 =94 R7 =92
 R8 =82 R9 =60 R10=87 R11=93 R12=83 R13=93 R14=97 R15=88

Photo Parameters:

$e=2.649e-002$ umol/s blue ratio=11.5 fluo. eff.= $2.694e-002$

Flux = 15.59 lm Eff. : 86.68 lm/W Fe = 52.67 mW

Electrical parameters:

VF = 2.998 V IF = 60.00 mA P = 179.9 mW Ch1



LEVEL:OUT WHITE:ANSI_2700K

Status: T=187.00ms Ip=39102 (60%) [HAAS2000_V1_USB] V2.00.220

Model:5050
 Tester:
 Temperature:25Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:48
 Date:2018-05-20 11-12
 Humidity:45%
 Remarks:

Spectrum Test Report



Color Parameters:

Chromaticity Coordinate: $x=0.4658$ $y=0.4095$ / $u'=0.2668$ $v'=0.5278$ $duv=-7.872e-004$
 Tc=2611K Dominant WL:Ld=584.9nm Purity=62.8%
 Ratio:R=27.8% G=70.4% B=1.8% Peak WL:Lp=628.0nm HWL:155.5nm
 Render Index:Ra=91.4 [暖白同1]
 R1 =92 R2 =94 R3 =95 R4 =92 R5 =91 R6 =93 R7 =92
 R8 =82 R9 =60 R10=86 R11=93 R12=82 R13=92 R14=97 R15=88

Photo Parameters:

$e=2.639e-002$ umol/s blue ratio=11.2 fluo. eff.= $2.694e-002$

Flux = 15.60 lm Eff. : 87.15 lm/W Fe = 52.53 mW

Electrical parameters:

VF = 2.984 V IF = 60.00 mA P = 179.0 mW Ch1

LEVEL:OUT WHITE:ANSI_2700K

Status: T=265.00ms Ip=54687 (83%) [HAAS2000_V1_USB] V2.00.220

Model:5050
 Tester:
 Temperature:25Deg
 Manufactory:
 Assessor:damin
 System:WY + HAAS2000_V1_USB

Number:49
 Date:2018-05-20 11-12
 Humidity:45%
 Remarks: